

Asphalt Cutback Specifications Sheet

PROPERTIES	ASTM	SC-800	SC-3000
	Test Method		
ORIGINAL BINDER		SPEC	SPEC
Viscosity	D-2170		
at 140 °F, CST			
Minimum		800	3000
Maximum		1600	6000
at 140 °F, CST, on Dist. Residue			
Minimum		20	40
Maximum		160	350
Flash Point in °F, COC	D-92	200	225
Distillation	D-402		
Total Distillates to 680 °F, Volume %			
Minimum		2.0	1.0
Maximum		12.0	5.0
Total Distillates to 500 °F, Volume %			
Maximum		0.5	0.5
Solubility	D-2042		
in Trichloroethelene wt. %		99.0	99.0
ASPHALT RESIDUE			
Residue of 100 Pen., %	D-243		
Minimum		70	80
Ductility of 100 Pen. Residue at 77 °F	D-113		
Minimum		100	100
Water %			
Maximum		0.5	0.5

T: 661-327-4257

F: 661-327-3236

3500 Shell Street, Bakersfield, CA 93308